

Claims

- [1] A decorative sheet for simultaneous decoration and injection molding, which is a laminate-type and which comprises a base film and at least a decorative layer provided on the base film, the decorative sheet having an elongation at break as measured at 25°C of 3 to 10%, and an elongation at break as measured at 120°C of 200% or more.
- [2] A decorative sheet for simultaneous decoration and injection molding according to claim 1, which has an elongation at break as measured at 25°C of 3 to 7%.
- [3] A decorative sheet for simultaneous decoration and injection molding according to claim 1 or 2, which has an elongation at break as measured at 120°C of 200 to 400%.
- [4] A decorative sheet for simultaneous decoration and injection molding according to any of claims 1 to 3, wherein the base film is formed of an acrylic resin composition.
- [5] A decorative sheet for simultaneous decoration and injection molding according to claim 4, wherein the acrylic resin composition is a resin composition containing, as a primary component, a polyacrylate and/or a polymethacrylate.
- [6] A decorated resin molded product comprising a resin molding, and a decorative sheet as recited in any of claims 1 to 5, the sheet being bonded onto the molding, wherein the decorative layer of the decorative sheet is bonded to the molding.